

TECHNICAL DATA SHEET

	Lux 40 Wood & Lux 80 Wood	
Blades		
Type of wood	Western Red Cedar	
Durability class	I-II	
Quality	Highest standard N°2 clears and better (flawless)	according to EN13659
Sawing	75-100% quarter sawn	according to EN13659
core- / sapwood	Only Core wood	
Drying	18% before sawing	
finish	None, the wood will grey naturally	
density	370 Kg/m ³	
Elastic Modulus	8000N/mm ²	
Radial shrinkage	0,30%	according to EN13659
Tangential shrinkage	0,70%	according to EN13659
Torsion	1%	according to EN13659
Origin	North-America & Canada	

